

Noise-Blok

Test & Leed Information

Physical Properties

Test	Test Method	Standard
Density/Weight	ASTM D412	1 lb. per FS
Tensile Strength	ASTM D412	500 PSI
Die "C" Tear	ASTM D412	100 LBS.
Shore A Durometer	ASTM D2240	80 +/-5
Burns Tests	Meets FMVSS302 UL-94 HF-1	Self Extinguishing Pass
Service Temperature		20°F to 180°F

Sound Transmission Class (STC)	ASTM E 90 (90A)	26
--------------------------------	-----------------	----

(LEED Information)

Vinyl recycled content	100%
Post Consumer Recycled Content	30%
Manufacturing Location	Chelsea, MA
Recyclable	100%

PRODUCT #	SOUND TRANSMISSION CLASS (dB FREQUENCY Hz)						STC
	125	250	500	1000	2000	4000	
	17	18	22	27	32	36	26

MADE WITH RECYCLED PVC



RECYCLED VINYL